

## TECHNICAL PRODUCT DATA

Product: Pebbled Aluminum

<b>POWDER PROPERTIES</b>		
SPECIFIC GRAVITY:	1.22 Calculated	
COVERAGE	79 .18 SQ.FT./LB. @ 2 MILS (100 % EFFICIENCY)	
PARTICLE SIZE	25 – 50 MICRONS AVE RAGE	
STORAGE	Store below 80 degrees, in cool dry environment	
<b>PHYSICAL PRODUCT TEST</b>		
GLOSS @ 60 DEGREES	D523	80% +/- 5%
DIRECT IMPACT	D2794	120 IN.LBS.
INDIRECT IMPACT	D2794	120 IN.LBS.
PENCIL HARDNESS	D3363	2H
CROSSHATCH ADHESION	D3359B	4B
FLEXIBILITY (CONICAL MANDREL)	D1737/D522	100%
<b>CHEMICAL AND CORROSION EXPOSURE TEST</b>		
CHEMICAL RESISTANCE	EXCELLENT RESISTANCE TO MOST SOLVENTS, OILS, ACIDS AND ALKALIES. SLIGHT YELLOWING IN WHITE AND PASTEL COLORS. ALL TEST PERFORMED ON 24 GAUGE BOND RITE 1000 PANELS.	PASS
RECYCLABILITY	THIS PRODUCT WAS DESIGNED TO BE RECLAIMED, SIEVED AND RECYCLED, IF PROPER HOUSEKEEPING IS MAINTAINED.	
Scratch and abrasion resistance	ASTM D7027,ASTM D4060	Pass
Accelerated weathering test	ISO 11341	5000 hours QUV Intended for internal use with exposure to filtered daylight

ALL PRODUCT, PRODUCT SPECIFICATIONS AND DATA ARE SUBJECT TO CHANGE WITHOUT NOTICE TO IMPROVE RELIABILITY, FUNCTION OR DESIGN OR OTHERWISE.

ATI and its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "ATI"), disclaim any and all liability for any errors, inaccuracies or incompleteness contained in any datasheet or in any other disclosure relating to any product.ATI makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product.

To the maximum extent permitted by applicable law, ATI disclaims (i) any and all liability arising out of the application or use of any product, (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Statements regarding the suitability of products for certain types of applications are based on ATI's knowledge of typical requirements that are often placed on ATI products in generic applications. Such statements are not binding statements about the suitability of products for a particular application. It is the customer's responsibility to validate that a particular product with the properties described in the product specification is suitable for use in a particular application.

Parameters provided in datasheets and / or specifications may vary in different applications and performance may vary over time.

All operating parameters, including typical parameters, must be validated for each customer application by the customer's technical experts. Product specifications do not expand or otherwise modify ATI's terms and conditions of purchase, including but not limited to the warranty expressed therein. Except as expressly indicated in writing, ATI products are not designed for use in medical, life-saving, or life-sustaining applications or for any other application in which the failure of the ATI product could result in personal injury or death. Customers using or selling ATI products not expressly indicated for use in such applications do so at their own risk. Please contact authorized ATI personnel to obtain written terms and conditions regarding products designed for such applications.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted by this document or by any conduct of ATI. Product names and markings noted herein may be trademarks of their respective owners.